

Application No.: 10/067,669  
Docket No.: FO-8038


Page 2

AMENDMENT

## In the Claims:

1. (Currently amended) An energy curable composition comprising:

a compound having  
the formula



wherein

R is the aromatic or heteroaromatic moiety;

Y is O or S;

R<sub>f</sub> includes the fluorinated alkylene, arylene or polyether moiety;

E is the ethylenically unsaturated moiety; and

n is 2, 3 or 4;

at least two fluorinated alkylene, arylene or polyether moieties, each fluorinated alkylene, arylene or polyether moiety being linked to the aromatic or heteroaromatic moiety through an ether or thioether;




at least one ethylenically unsaturated moiety, each ethylenically unsaturated moiety being linked to one of the fluorinated alkylene, arylene or polyether moieties; and wherein the composition has an absorption loss of less than 0.5 dB/cm at a wavelength of 1550 nm.

2. (Cancelled)




Application No.: 10/067,669  
 Docket No.: FO-8038

Page 3

3. (Original) The energy curable composition of claim 1 wherein the compound has a formula selected from the group



consisting of



wherein






each R is an aromatic or heteroaromatic moiety;  
 each Y is O or S; each Rf includes a fluorinated  
 alkylene moiety, a fluorinated arylene moiety, or a fluorinated  
 polyether moiety;

Application No.: 10/067,669  
Docket No.: FO-8038

Page 4



















each E is an ethylenically unsaturated moiety;  
each j is 1, 2, or 3;  
each m is 1, 2 or 3;  
each n subscript is 0, 1, 2, 3 or 4; and  
the sum of the n subscripts in each formula is 2, 3  
or 4.

4. (Original) The energy curable composition of claim 1 wherein the aromatic or heteroaromatic moiety is selected from the group consisting of




Application No.: 10/067,669  
Docket No.: FO-8038

Page 5



Application No.: 10/067,669  
 Docket No.: FO-8038

Page 6



5. (Previously amended) The energy curable composition of claim 1 wherein the fluorinated alkylene, arylene or polyether moiety is selected from the group consisting of

- $(CF_2)_x$ -
- $(C_6F_4)_x$ -
- $CF_2O-[(CF_2CF_2O)_m(CF_2O)_n]-CF_2$ -
- $CF(CF_3)O(CF_2)_4O[CF(CF_3)CF_2O]_pCF(CF_3)$ -
- $CF_2O-(CF_2CF_2O)_m-CF_2$ -

wherein x is an integer between 1 and about 10;  
 m and n designate the number of randomly distributed perfluoroethyleneoxy and perfluoromethyleneoxy backbone repeating subunits, respectively; and  
 p designates the number of  $-CF(CF_3)CF_2O-$  backbone repeating subunits.

6. (Original) The energy curable composition of claim 1 wherein each ethylenically unsaturated moiety is selected from the group consisting of acrylate, methacrylate, haloacrylate, halomethacrylate, vinyl ether and allyl ether.

7. (Original) The energy curable composition of claim 1 having a  $C_H$  of less than about 55 M.


8. (Original) The energy curable composition of claim 1 having a  $C_H$  of less than about 20 M.

9. (Original) The energy curable composition of claim 1 having a  $C_H$  of less than about 10 M.

Application No.: 10/067,669  
Docket No.: FO-8038

Page 7

10. (Original) The energy curable composition of claim 1 having an absorption loss of less than about 0.5 dB/cm at 1550 nm.
11. (Original) The energy curable composition of claim 1 having an absorption loss of less than about 0.2 dB/cm at 1550 nm.
12. (Original) The energy curable composition of claim 1 having an absorption loss of less than about 0.1 dB/cm at 1550 nm.
13. (Original) The energy curable composition of claim 1 further including an initiator.
14. (Original) The energy curable composition of claim 1 wherein the compound is present in an amount of at least about 10% by weight.
15. (Withdrawn) An energy curable composition comprising:  
a compound having an isocyanurate moiety,  
three fluoriated alkylene, arylene, or polyether moieties linked to the isocyanurate moiety at the nitrogens of the isocyanurate, and at least one ethylenically unsaturated moiety linked to one of the fluorinated alkylene, arylene, or polyether moieties.
16. (Withdrawn) The energy curable composition of claim 15 comprising  
a compound having the formula









Application No.: 10/067,669  
 Docket No.: FO-8038

Page 8

wherein Rf includes a fluorinated alkylene, arylene or polyether moiety and E is an ethylenically unsaturated moiety.

17. (Withdrawn) The energy curable composition of claim 15 wherein the compound has a formula selected from the group consisting of



wherein  $\text{C}_3\text{N}_3\text{O}_3$  is the isocyanurate nucleus; each Rf includes a fluorinated alkylene moiety, a fluorinated arylene moiety, or a fluorinated polyether moiety; each E is an ethylenically unsaturated moiety; each n subscript is 0, 1, 2 or 3; and the sum of the n subscripts in each formula is 3.

Application No.: 10/067,669  
Docket No.: FO-8038

Page 9

18. (Withdrawn) The energy curable composition of claim 15 wherein the fluorinated alkylene, arylene or polyether moiety is selected from the group consisting of

- (CF<sub>2</sub>)<sub>x</sub>- ,
- (C<sub>6</sub>F<sub>4</sub>)<sub>x</sub>-
- CF<sub>2</sub>O- [(CF<sub>2</sub>CF<sub>2</sub>O)<sub>m</sub>(CF<sub>2</sub>O)<sub>n</sub>]-CF<sub>2</sub>- ,
- CF(CF<sub>3</sub>)O(CF<sub>2</sub>)<sub>4</sub>O[CF(CF<sub>3</sub>)CF<sub>2</sub>O]<sub>p</sub>CF(CF<sub>3</sub>)- , and
- CF<sub>2</sub>O-(CF<sub>2</sub>CF<sub>2</sub>O)<sub>m</sub>-CF<sub>2</sub>- ,

wherein x is an integer between 1 and about 10;  
m and n designate the number of randomly distributed perfluoroethyleneoxy and perfluoromethyleneoxy backbone repeating subunits, respectively; and  
p designates the number of -CF(CF<sub>3</sub>)CF<sub>2</sub>O- backbone repeating subunits.

19. (Withdrawn) The energy curable composition of claim 15 wherein each ethylenically unsaturated moiety is selected from the group consisting of acrylate, methacrylate, haloacrylate, halomethacrylate, vinyl ether and allyl ether.

20. (Withdrawn) The energy curable composition of claim 15 having a C<sub>H</sub> of less than about 55 M.

21. (Withdrawn) The energy curable composition of claim 15 having a C<sub>H</sub> of less than about 20 M.

22. (Withdrawn) The energy curable composition of claim 15 having a C<sub>H</sub> of less than about 10 M.

23. (Withdrawn) The energy curable composition of claim 15 wherein the compound is present in an amount of at least 10% by weight.




Application No.: 10/067,669  
Docket No.: FO-8038

Page 10

24. (Original) A polymeric material, the polymeric material comprising a polymer or copolymer of an energy curable composition, the energy curable composition having  
an aromatic or heteroaromatic moiety;  
at least two fluorinated alkylene, arylene or polyether moieties, each fluorinated alkylene, arylene or polyether moiety being linked to the aromatic or heteroaromatic moiety through an ether or thioether;  
at least one ethylenically unsaturated moiety, each ethylenically unsaturated moiety being linked to one of the fluorinated alkylene, arylene or polyether moieties.

25. (Original) The polymeric material of claim 24 wherein the energy curable compound has the formula



wherein

R is the aromatic or heteroaromatic moiety;


Y is O or S;

R<sub>f</sub> includes the fluorinated alkylene, arylene or polyether moiety;

E is the ethylenically unsaturated moiety; and















n is 2, 3 or 4.

26. (Original) The polymeric material of claim 24 wherein the aromatic or heteroaromatic moiety is selected from the group consisting of




Application No.: 10/067,669  
Docket No.: FO-8038

Page 11



Application No.: 10/067,669  
 Docket No.: FO-8038

Page 12



and

27. (Original) The polymeric material of claim 24 wherein the fluorinated alkylene, arylene or polyether moiety is selected from the group consisting of

- (CF<sub>2</sub>)<sub>x</sub>-,
- (C<sub>6</sub>F<sub>4</sub>)<sub>x</sub>-,
- CF<sub>2</sub>O-[(CF<sub>2</sub>CF<sub>2</sub>O)<sub>m</sub>(CF<sub>2</sub>O)<sub>n</sub>]-CF<sub>2</sub>-,
- CF(CF<sub>3</sub>)O(CF<sub>2</sub>)<sub>4</sub>O[CF(CF<sub>3</sub>)CF<sub>2</sub>O]<sub>p</sub>CF(CF<sub>3</sub>)-, and
- CF<sub>2</sub>O-(CF<sub>2</sub>CF<sub>2</sub>O)<sub>m</sub>-CF<sub>2</sub>-,

wherein x is an integer between 1 and about 10;

Application No.: 10/067,669  
Docket No.: FO-8038

Page 13

m and n designate the number of randomly distributed perfluoroethyleneoxy and perfluoromethyleneoxy backbone repeating subunits, respectively; and p designates the number of  $-\text{CF}(\text{CF}_3)\text{CF}_2\text{O}-$  backbone repeating subunits.

28. (Original) The polymeric material of claim 24 having a  $C_n$  of less than about 55 M

29. (Original) The polymeric material of claim 24 having a  $C_n$  of less than about 20 M.

30. (Original) The polymeric material of claim 24 having a  $C_n$  of less than about 10 M.


31. (Original) The polymeric material of claim 24 having an absorption loss of less than about 0.5 dB/cm at 1550 nm.

32. (Withdrawn) A polymeric material, the polymeric material comprising a polymer or copolymer of an energy curable composition including

a compound having an isocyanurate moiety,  
three fluorinated alkylene, arylene, or polyether moieties linked to the isocyanurate moiety at the nitrogens of the isocyanurate, and

at least one ethylenically unsaturated moiety linked to one of the fluorinated alkylene, arylene, or polyether moieties.

33. (Withdrawn) The polymeric material of claim 32 wherein the energy curable compound has the formula



Application No.: 10/067,669  
Docket No.: FO-8038

Page 14

wherein Rf includes a fluorinated alkylene, arylene or polyether moiety and E is an ethylenically unsaturated moiety.

34. (Withdrawn) The polymeric material of claim 32 wherein the fluorinated alkylene, arylene or polyether moiety is selected from the group consisting of

- (CF<sub>3</sub>)<sub>x</sub>- ,
- (C<sub>6</sub>F<sub>4</sub>)<sub>x</sub>-
- CF<sub>2</sub>O- [(CF<sub>2</sub>CF<sub>2</sub>O)<sub>m</sub>(CF<sub>2</sub>O)<sub>n</sub>]-CF<sub>2</sub>- ,
- CF(CF<sub>3</sub>)O(CF<sub>2</sub>)<sub>4</sub>O[CF(CF<sub>3</sub>)CF<sub>2</sub>O]<sub>p</sub>CF(CF<sub>3</sub>)- , and
- CF<sub>2</sub>O-(CF<sub>2</sub>CF<sub>2</sub>O)<sub>m</sub>-CF<sub>2</sub>- ,

wherein x is an integer between 1 and about 10;  
m and n designate the number of randomly distributed perfluoroethyleneoxy and perfluoromethyleneoxy backbone repeating subunits, respectively; and  
p designates the number of -CF(CF<sub>3</sub>)CF<sub>2</sub>O- backbone repeating subunits.

35. (Withdrawn) The polymeric material of claim 32 having a C<sub>H</sub> of less than about 55 M

36. (Withdrawn) The polymeric material of claim 32 having a C<sub>H</sub> of less than about 20 M.

37. (Withdrawn) The polymeric material of claim 32 having a C<sub>H</sub> of less than about 10 M.

38. (Withdrawn) The polymeric material of claim 32 having an absorption loss of less than about 0.5 dB/cm at 1550 nm.

39. (Original) An optical element comprising a polymeric core, the polymeric core including a polymer or copolymer of an energy curable compound having an aromatic or heteroaromatic moiety;

Application No.: 10/067,669  
Docket No.: FO-8038

Page 15

at least two fluorinated alkylene, arylene or polyether moieties, each fluorinated alkylene, arylene or polyether moiety being linked to the aromatic or heteroaromatic moiety through an ether or thioether;

at least one ethylenically unsaturated moiety, each ethylenically unsaturated moiety being linked to one of the fluorinated alkylene, arylene or polyether moieties.

40. (Original) The optical element of claim 39 wherein the fluorinated alkylene, arylene or polyether moiety is selected from the group consisting of

- (CF<sub>2</sub>)<sub>x</sub>- ,
- (C<sub>6</sub>F<sub>4</sub>)<sub>x</sub>-
- CF<sub>2</sub>O- [(CF<sub>2</sub>CF<sub>2</sub>O)<sub>m</sub>(CF<sub>2</sub>O)<sub>n</sub>]-CF<sub>2</sub>- ,
- CF(CF<sub>3</sub>)O(CF<sub>2</sub>)<sub>4</sub>O[CF(CF<sub>3</sub>)CF<sub>2</sub>O]<sub>p</sub>CF(CF<sub>3</sub>)- , and
- CF<sub>2</sub>O- (CF<sub>2</sub>CF<sub>2</sub>O)<sub>m</sub>-CF<sub>2</sub>- ,

wherein x is an integer between 1 and about 10;  
m and n designate the number of randomly distributed perfluoroethyleneoxy and perfluoromethyleneoxy backbone repeating subunits, respectively; and  
p designates the number of -CF(CF<sub>3</sub>)CF<sub>2</sub>O- backbone repeating subunits.

41. (Original) The optical element of claim 39 wherein the polymeric core has a C<sub>H</sub> of less than about 55 M.


42. (Original) The optical element of claim 39 wherein the polymeric core has an absorption loss of less than about 0.5 dB/cm at 1550 nm.

Application No.: 10/067,669  
Docket No.: FO-8038

Page 16

43. (Withdrawn) An optical element comprising a polymeric core, the polymeric core including a polymer or copolymer of an energy curable compound having an isocyanurate moiety, three fluorinated alkylene, arylene, or polyether moieties linked to the isocyanurate moiety at the nitrogens of the isocyanurate, and at least one ethylenically unsaturated moiety linked to one of the fluorinated alkylene, arylene, or polyether moieties.

44. (Withdrawn) The optical element of claim 43 wherein the fluorinated alkylene, arylene or polyether moiety is selected from the group consisting of



wherein  $x$  is an integer between 1 and about 10;  
 $m$  and  $n$  designate the number of randomly distributed perfluoroethyleneoxy and perfluoromethyleneoxy backbone repeating subunits, respectively; and  
 $p$  designates the number of  $-\text{CF}(\text{CF}_3)\text{CF}_2\text{O}-$  backbone repeating subunits.

45. (Withdrawn) The optical element of claim 43 wherein the polymeric core has a  $C_H$  of less than about 55 M.

46. (Withdrawn) The optical element of claim 43 wherein the polymeric core has an absorption loss of less than about 0.5 dB/cm at 1550 nm.